

# Stanyl® TW300

## PA46

Heat Stabilized

Print Date: 2025-10-23

Stanyl® TW300 is a non-reinforced high heat polyamide that offers excellent wear & friction properties in combination with outstanding creep resistance, strength, stiffness and fatigue resistance especially at high temperatures in combination with cycle-time advantages and excellent flow.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
<b>RHEOLOGICAL PROPERTIES</b>			
	<b>DRY / COND</b>		
Molding shrinkage [parallel]	2 / *	%	Sim. to ISO 294-4
Molding shrinkage [normal]	2 / *	%	Sim. to ISO 294-4
<b>MECHANICAL PROPERTIES</b>			
	<b>DRY / COND</b>		
Tensile modulus	3300 / 1000	MPa	ISO 527-1/-2
Tensile modulus (120°C)	800 / –	MPa	ISO 527-1/-2
Tensile modulus (160°C)	650	MPa	ISO 527-1/-2
Tensile modulus (180°C)	600	MPa	ISO 527-1/-2
Tensile modulus (200°C)	500	MPa	ISO 527-1/-2
Yield stress	100 / 55	MPa	ISO 527-1/-2
Yield stress (120°C)	50	MPa	ISO 527-1/-2
Yield stress (160°C)	40	MPa	ISO 527-1/-2
Yield stress (180°C)	35	MPa	ISO 527-1/-2
Yield stress (200°C)	30	MPa	ISO 527-1/-2
Nominal strain at break	40 / >50	%	ISO 527-1/-2
Nominal strain at break (120°C)	>50	%	ISO 527-1/-2
Nominal strain at break (160°C)	>50	%	ISO 527-1/-2
Nominal strain at break (180°C)	>50	%	ISO 527-1/-2
Nominal strain at break (200°C)	>50	%	ISO 527-1/-2
Flexural modulus	3000 / 900	MPa	ISO 178
Flexural modulus (120°C)	800	MPa	ISO 178

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

# Stanyl® TW300

Print Date: 2025-10-23

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Flexural modulus (160°C)	600	MPa	ISO 178
Flexural strength	150 / 50	MPa	ISO 178
Flexural strength (120°C)	50	MPa	ISO 178
Flexural strength (160°C)	40	MPa	ISO 178
Charpy impact strength (+23°C)	N / N	kJ/m²	ISO 179/1eU
Charpy impact strength (−30°C)	N / N	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	10 / 35	kJ/m²	ISO 179/1eA
Charpy notched impact strength (−30°C)	4 / 4	kJ/m²	ISO 179/1eA
Izod notched impact strength (+23°C)	10 / 35	kJ/m²	ISO 180/1A
Izod notched impact strength (−40°C)	4 / 4	kJ/m²	ISO 180/1A

THERMAL PROPERTIES	DRY / COND		
Melting temperature (10°C/min)	295 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	190 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	280 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.75 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.8 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
UL recognition	Yes / *	—	—
Burning Behav. at 3.0 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	3 / *	mm	IEC 60695-11-10
UL recognition	Yes / *	—	—
Relative Temperature Index – electrical	150	°C	UL746B
RTI electrical (Thickness (1) tested)	0.75	mm	UL746B
Thermal Index 5000 hrs	152	°C	IEC 60216/ISO 527-1/-2

ELECTRICAL PROPERTIES	DRY / COND		
Volume resistivity	1E13 / 1E7	Ohm*m	IEC 62631-3-1

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied. Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect. Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.


# Stanyl® TW300

Print Date: 2025-10-23

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Electric strength	25 / 15	kV/mm	IEC 60243-1
Comparative tracking index	400 / -	V	IEC 60112
Relative permittivity (100Hz)	3.9 / 22	-	IEC 62631-2-1
Relative permittivity (1 MHz)	3.6 / 4.5	-	IEC 62631-2-1

OTHER PROPERTIES	DRY / COND		
Humidity absorption	3.7 / *	%	Sim. to ISO 62
Density	1180 / -	kg/m³	ISO 1183

Tens. fatigue 8Hz, T, R=0.1 ,  
dry



Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.  
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.  
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.  
Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.