

Stanyl® TW363

PA46-I

Heat Stabilized, Impact Modified

Print Date: 2024-09-17

Stanyl® TW363 is an impact-modified high heat polyamide that offers excellent wear & friction properties in combination with outstanding creep resistance, strength, stiffness and fatigue resistance especially at high temperatures in combination with cycle-time advantages and excellent flow.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage [parallel]	2 / *	%	Sim. to ISO 294-4
Molding shrinkage [normal]	2 / *	%	Sim. to ISO 294-4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	1850 / 600	MPa	ISO 527-1/-2
Tensile modulus (120°C)	400 / -	MPa	ISO 527-1/-2
Tensile modulus (160°C)	350	MPa	ISO 527-1/-2
Yield stress	60 / 45	MPa	ISO 527-1/-2
Yield stress (120°C)	35	MPa	ISO 527-1/-2
Yield stress (160°C)	30	MPa	ISO 527-1/-2
Nominal strain at break	>50 / >50	%	ISO 527-1/-2
Nominal strain at break (120°C)	>50	%	ISO 527-1/-2
Nominal strain at break (160°C)	>50	%	ISO 527-1/-2
Flexural modulus	1800 / 550	MPa	ISO 178
Flexural modulus (120°C)	400	MPa	ISO 178
Flexural modulus (160°C)	350	MPa	ISO 178
Flexural strength	80 / 40	MPa	ISO 178
Flexural strength (120°C)	40	MPa	ISO 178
Flexural strength (160°C)	30	MPa	ISO 178
Charpy impact strength (+23°C)	N / N	kJ/m²	ISO 179/1eU

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data

Stanyl® TW363

Print Date: 2024-09-17

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
Charpy impact strength (-30°C)	N / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	75 / 125	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	26 / 30	kJ/m ²	ISO 179/1eA
Izod notched impact strength (+23°C)	80 / 125	kJ/m ²	ISO 180/1A
Izod notched impact strength (-40°C)	40 / 40	kJ/m ²	ISO 180/1A
<i>THERMAL PROPERTIES</i>		<i>DRY / COND</i>	
Melting temperature (10°C/min)	295 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	90 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	200 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	1.6 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.8 / *	E-4/°C	ISO 11359-1/-2
Thermal Index 5000 hrs	135	°C	IEC 60216/ISO 527-1/-2
<i>ELECTRICAL PROPERTIES</i>		<i>DRY / COND</i>	
Volume resistivity	1E13 / 1E7	Ohm*m	IEC 62631-3-1
Electric strength	25 / 15	kV/mm	IEC 60243-1
Comparative tracking index	475 / -	V	IEC 60112
Relative permittivity (100Hz)	3.6 / 14	-	IEC 62631-2-1
Relative permittivity (1 MHz)	3.2 / 4	-	IEC 62631-2-1
<i>OTHER PROPERTIES</i>		<i>DRY / COND</i>	
Humidity absorption	2.95 / *	%	Sim. to ISO 62
Density	1100 / -	kg/m ³	ISO 1183

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.