

Tepex® dynalite 207-C200(x)/50%

PPS-CF58

=+/ 4+ 44

Print Date: 2025年12月11日

Tepex® dynalite 207-C200(x)/50% 3K Carbon - PPS consolidated composite laminate



The datasheet is valid for this specific composition only, the characteristics of composites depend on reinforcement level and fiber orientation. Non-standard thickness may alter some or all of these properties. The data listed here are given as average product properties and should not be used to establish specification limits nor used alone as basis of design. The underlying tests were conducted at room temperature and (where possible) with 2 mm specimen thickness. For tensile and flexural tests a specimen width of 25 mm was used and is highly recommended to achieve representative results.

	代表值	単位	試験方法
0	値		
繊維	3K Carbon		
Weaving style	Twill 2/2		DIN ISO 9354
Area weight (dry fabric)	200	g/m²	DIN EN 12127
Weight rate (0°/90°)	50/50	%/%	
Fiber volume content	50	vol.–%	nominal
層あたりの厚さ	0.22	mm	nominal
機械特性	乾燥/調湿		
引張弹性率	52 / -	GPa	ISO 527-4/5
引張強度	750 / -	MPa	ISO 527-4/5
Elongation at Break	1.3 / -	%	ISO 527-4/5
曲げ弾性率	46 / -	GPa	ISO 14125
曲げ強度	830 / -	MPa	ISO 14125
熱的特性	乾燥/調湿		
密度	1560 / -	kg/m³	ISO 1183
ガラス転移温度 (10℃/min)	91 / *	°C	ISO 11357-1/-2

Tepex® dynalite 207-C200(x)/50%

Print Date: 2025年12月11日

諸特性	代表值	単位	試験方法
融点 (10℃/min)	280 / *	°C	ISO 11357-1/-3
熱変形温度 (0.1% 曲げ弾性率)	270	°C	ISO 75-1/3
1.5mm厚さでの燃焼性	V-0 / *	class	IEC 60695-11-10
追加試験片の厚さ (1.5)	1.5 / *	mm	IEC 60695-11-10
厚さhでの燃焼性	V-0 / *	class	IEC 60695-11-10
追加試験片の厚さ(h)	3 / *	mm	IEC 60695-11-10
厚さhでの燃焼性	V-0 / *	class	IEC 60695-11-10
追加試験片の厚さ	0.4 / *	mm	IEC 60695-11-10
厚さhでの燃焼性	V-0 / *	class	IEC 60695-11-10
試験片厚さ	0.75 / *	mm	IEC 60695-11-10
CLTE -35°C to 23°C (0°)	3.8	E-6/°C	ISO 11359-1/-2
CLTE 23°C to 80°C (0°)	3.7	E-6/°C	ISO 11359-1/-2