

UDea™ Akulon® K20HG60

PA6–GF60

60% Continuous Glass Fiber Reinforced, Uni–Directional Tape, Heat Stabilized, Black

Print Date: 2024–07–03

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
GENERAL PHYSICAL PROPERTIES			
	DRY / COND		
Density	1700 / –	kg/m ³	ISO 1183
Fiber content (wt%)	60	%	ISO 11667
Fiber content (V/V)	39.5	%	ISO 11667
PHYSICAL TAPE PROPERTIES			
	VALUE		
Areal weight – Tape	426	g/m ²	ISO 1172
Thickness – Tape	0.25	mm	
MECHANICAL TAPE PROPERTIES			
	DRY / COND		
Tensile modulus – 0° – Tape	31.5 / 30	GPa	ISO 527–4/–5
Stress at break – 0° – Tape	800 / 650	MPa	ISO 527–4/–5
Strain at break – 0° – Tape	2.7 / 2.3	%	ISO 527–4/–5
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357–1/–3
Glass transition temperature (10°C/min)	60 / *	°C	ISO 11357–1/–2
OTHER PROPERTIES			
	DRY / COND		
Humidity absorption	1 / *	%	Sim. to ISO 62

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.