

Xytron™ G4080HRE

PPS-I-GF40

Print Date: 2024-03-27

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
RHEOLOGICAL PROPERTIES			
	VALUE		
Molding shrinkage (parallel)	0.2	%	ISO 294-4
Molding shrinkage (normal)	0.5	%	ISO 294-4
MECHANICAL PROPERTIES			
	VALUE		
Tensile modulus	13300	MPa	ISO 527-1/-2
Tensile modulus (120°C)	6100	MPa	ISO 527-1/-2
Tensile modulus (160°C)	4700	MPa	ISO 527-1/-2
Tensile modulus (200°C)	4000	MPa	ISO 527-1/-2
Stress at break	180	MPa	ISO 527-1/-2
Stress at break (120°C)	80	MPa	ISO 527-1/-2
Stress at break (160°C)	60	MPa	ISO 527-1/-2
Stress at break (200°C)	46	MPa	ISO 527-1/-2
Strain at break	2.4	%	ISO 527-1/-2
Strain at break (120°C)	4.1	%	ISO 527-1/-2
Strain at break (160°C)	4.3	%	ISO 527-1/-2
Strain at break (200°C)	3.9	%	ISO 527-1/-2
Flexural modulus	12200	MPa	ISO 178
Flexural strength	267	MPa	ISO 178
Flexural modulus (120°C)	5900	MPa	ISO 178
Flexural modulus (160°C)	4600	MPa	ISO 178
Flexural modulus (200°C)	4000	MPa	ISO 178
Charpy impact strength (+23°C)	60	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	65	kJ/m ²	ISO 179/1eU

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data

Xytron™ G4080HRE

Print Date: 2024-03-27

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Charpy notched impact strength (+23°C)	13	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	12	kJ/m ²	ISO 179/1eA
Izod impact strength (+23°C)	60	kJ/m ²	ISO 180/1U
Izod notched impact strength (+23°C)	16	kJ/m ²	ISO 180/1A
Izod notched impact strength (-40°C)	13	kJ/m ²	ISO 180/1A
Rockwell hardness, R scale	117	–	ISO 2039-2

THERMAL PROPERTIES	VALUE		
Melting temperature (10°C/min)	280	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	266	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.15	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.48	E-4/°C	ISO 11359-1/-2
Coef. of lin. therm expansion, parallel, above Tg	0.11	E-4/°C	ISO 11359-1/-2
Coef. of lin. therm expansion, normal, above Tg	1.1	E-4/°C	ISO 11359-1/-2
Burning Behav. at 3.0 mm nom. thickn.	V-0	class	IEC 60695-11-10
UL recognition	Yes	–	–

ELECTRICAL PROPERTIES	VALUE		
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Electric strength	33	kV/mm	IEC 60243-1
Comparative tracking index	175	V	IEC 60112
Dissipation factor (5GHz)	55	E-4	IEC 61189-2-721
Relative permittivity (5GHz)	3.8	–	IEC 61189-2-721

OTHER PROPERTIES	VALUE		
Density	1600	kg/m ³	ISO 1183

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.