

# Novamid<sup>®</sup> 1013C5

## PA6

Injection Molding, Molding Release, Improved Processing, Lubricated, Nucleated

Print Date: 2024-03-27

Good and fast flow-ability. Very easy mold release. Medium viscosity in injection molding grades. Ideal for high cycle injection molding production.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
<b>RHEOLOGICAL PROPERTIES</b>			
	<b>DRY / COND</b>		
Molding shrinkage [parallel]	1.2 / *	%	Sim. to ISO 294-4
Molding shrinkage [normal]	1.3 / *	%	Sim. to ISO 294-4
<b>MECHANICAL PROPERTIES</b>			
	<b>DRY / COND</b>		
Tensile modulus	3100 / 1300	MPa	ISO 527-1/-2
Yield stress	82 / 50	MPa	ISO 527-1/-2
Nominal strain at break	18 / >50	%	ISO 527-1/-2
Flexural modulus	2800 / 1100	MPa	ISO 178
Flexural strength	110 / 54	MPa	ISO 178
Charpy impact strength (+23°C)	N / -	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)	3 / 26	kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL PROPERTIES</b>			
	<b>DRY / COND</b>		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	75 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	169 / *	°C	ISO 75-1/-2
Burning Behav. at 1.5 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Burning Behav. at 3.0 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	3 / *	mm	IEC 60695-11-10

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

## Property Data

# Novamid<sup>®</sup> 1013C5

Print Date: 2024-03-27

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<b><i>ELECTRICAL PROPERTIES</i></b>			
Relative permittivity (100Hz)	4 / –	–	IEC 62631-2-1
Relative permittivity (1 MHz)	4 / –	–	IEC 62631-2-1
Dissipation factor (100 Hz)	110 / –	E-4	IEC 62631-2-1
Dissipation factor (1 MHz)	220 / –	E-4	IEC 62631-2-1
Volume resistivity	>1E13 / –	Ohm*m	IEC 62631-3-1
Surface resistivity	– / 2E14	Ohm	IEC 62631-3-2
Electric strength	26 / –	kV/mm	IEC 60243-1
Comparative tracking index	600 / –	V	IEC 60112
<b><i>OTHER PROPERTIES</i></b>			
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1130 / –	kg/m <sup>3</sup>	ISO 1183
<b><i>MATERIAL SPECIFIC PROPERTIES</i></b>			
Viscosity number	133 / *	cm <sup>3</sup> /g	ISO 307, 1157, 1628

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

# Novamid® 1013C5

Print Date: 2024-03-27

## Viscosity-shear rate

